

CHESTERTON® 100 PRODUCT DATA SHEET

1.0 COMPOSITION

Styrene Butadiene Rubber (SBR) sheet compounded to remain soft and pliable.

2.0 USAGE

This material is particularly suitable for air, hot water, cold water and low pressure steam up to temperatures of 180° F (82°C).

3.0 TYPICAL PROPERTIES

- A. Width – 36” +/- 1” (91,4cm +/- 2,5cm)
- B. Thickness, Inches – 1/16, 3/32, 1/8, 3/16, 1/4
Millimeters - 1,6, 2,4, 3,2, 4,8, 6,4
- C. Tensile Strength, minimum, PSI (Bar) – 700 (48)
- D. Hardness, Durometer, Shore A – 70-85
- E. Elongation – 200%, minimum
- F. Specific Gravity, Typical – 1.78 g/cc
- G. Pressure Rating, maximum, 1/8” (3,2mm) thick – 250 PSI (17 Bar)
- H. Color – Red
- I. Finish – Smooth

A.W.CHESTERTON CO.

860 Salem Street
Groveland, MA 01834 USA
Telephone: 781-438-7000
Fax: 978-469-6528
www.chesterton.com

©A.W.Chesterton Company,2007. All rights reserved.
®Registered trademark owned and licensed by
A.W.Chesterton Company in USA and other countries.

FORM NO. E72024

PRINTED IN USA 02/08